



Lonestar Alpha Laboratories

Muscat : P.O. Box 1197, P.C 130, Muscat, Sultanate of Oman - Tel.: +968 24501524 / 5590, Fax : +968 24503814
Sohar : P.O. Box 84, P.C 327, Sohar Industrial Estate, Sultanate of Oman - Tel.: +968 26751755 / 920 / 976, Fax : +968 26751331
Duqm : Tel.: +968 99278040, E-mail: duqm.lab@lonestaralpha.com - Salalah : Tel.: +968 99887835, E-mail: salalah.lab@lonestaralpha.com
E-mail : info@lonestaralpha.com, Website: www.lonestaralpha.com

REPORT ON COMPRESSIVE STRENGTH OF CONCRETE MASONRY BLOCKS

REPORT NO.	LSCIV09-9127/2	REPORT DATE	29.01.13
REQUEST NO.	SCIV/13-0116/2	SAMPLE NO.	SCIV/13-0116/2
CUSTOMER	AL SALAMI & AL KASHRY TRADING CO.LLC	DATE OF RECEIPT	15.01.13
PROJECT CLIENT	NG	CONSULTANT	NG
PROJECT	FOR VARIOUS PROJECTS	LOCATION	OUHI
SAMPLE DESCRIPTION	8" SOLID BLOCK (10.5N/MM ²)	NOMINAL SIZE mm	390 X 190 X 190
PLACE OF SAMPLING	SITE	SOURCE	SOHAR PLANT
METHOD OF SAMPLING	NG	DATE OF SAMPLING	15.01.13
SAMPLE BROUGHT IN BY	CUSTOMER	CERTIFICATE OF SAMPLING	NG
PRODUCTION DATE	01.01.13	CLIENT REF	NG
TESTED BY	SMS	VERIFIED BY	RMP
TEST METHOD	BS 6073: PART 1 & 2: 1981	TEST METHOD VARIATION (IF ANY)	NIL
REMARK (IF ANY)	NIL	PAGE #	1 OF 1

SPECIMEN NO.	AVERAGE THICKNESS mm	AREA mm ²	MAXIMUM LOAD kN	CRUSHING STRENGTH N/mm ²
1	190	74100	1113	15.0
2	190	74100	1320	17.8
3	190	74100	1170	15.8
4	190	74100	1210	16.3
5	190	74100	1245	16.8
6	190	74100	1260	17.0
7	190	74100	1245	16.8
8	190	74100	1301	17.6
9	190	74100	1285	17.3
10	190	74100	1140	15.4
AVERAGE COMPRESSIVE STRENGTH N/mm ²				16.6

Note: Cement type used: OPC

Rakesh M. Pillai
Assist. Manager - Civil

For and on Behalf of Lonestar Alpha Laboratories
Sohar

NOTE : This report shall be reproduced in full. Approval of the testing Laboratory is required for partial reproduction. The test results relate only to the sample tested.

